

Mylar® A 190 - 500μm

Product Description

MYLAR® polyester film is a flexible, strong and durable film with an unusual balance of properties making it suitable for many industrial applications. Type MYLAR® A is a tough general purpose film available in $12\mu m$ to $500\mu m$ thickness range. In film thickness $12\mu m$ to $125\mu m$, MYLAR® A is slightly hazy. In film thicknesses $190\mu m$ and above, MYLAR® A is hazy. Type MYLAR® A is primarily used for release applications, office supplies, electrical insulation and industrial laminations with other flexible materials.

Film Properties (typical values)

Type MYLAR® A has a tensile strength that averages 210 MPa, has excellent resistance to moisture and most chemicals and can withstand temperature extremes from -70°C to 150°C. Because it contains no plasticisers MYLAR® Adoes not become brittle with age under normal conditions.

Property	Test Method		Value				
Thickness		micron	190	250	300	350	500
Tensile Strength (Mpa)	ASTM D 882	MD	190	190	190	190	150
• • • •		TD	220	200	200	190	170
Modulus (Mpa)	ASTM D 882	MD	3300	3100	3000	2950	2600
• 1		TD	3700	3500	3200	3200	2800
Elongation (%)	ASTM D 882	MD	190	210	210	240	270
		TD	140	170	180	200	240
Shrinkage 150°C for 30 min (%)	ASTM D 1204	MD	1.3	1.3	1.3	1.3	0.9
. /		TD	1.3	1.3	1.3	1.3	0.9
Shrinkage 200°C for 30 min (%)	ASTM D 1204	MD	3.5	3.5	3.5	3.5	2
		TD	3.3	3.3	3.5	3.3	1.7
Haze (%)	ASTM D 1003		82	90	92	96	97
	Gardner Hazemeter						
Dielectric Strength	ASTM D 149		17.5	19	19.5	20	20
(minimum) (kV)	1 MD Madia						,

1mm = 1 micron = 0.001 mm approx 4 gauge, MD = Machine Direction, TD = Transverse Direction